

* NOTE: This is the abstract for BOTH

WO 9946218 & AT 9800403

L3 ANSWER 19 OF 71 CA COPYRIGHT 2003 ACS on STN
AN 131:218272 CA
TI Electrically conductive coating for microcapillary composite matrices, and their formation
IN Schwarz, Wolfgang
PA Austria
SO PCT Int. Appl., 28 pp.
CODEN: PIXXD2
DT Patent
LA German
IC ICM C04B041-00
CC 58-2 (Cement, Concrete, and Related Building Materials)
FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	WO 9946218	A2	19990916	WO 1999-AT56	19990308
	WO 9946218	A3	20000302		
	W:	AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, AM, AZ, BY, KG, KZ, MD, RU, TJ, TM			
	RW:	GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW, AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG			
	AT 9800403	A	19990915	AT 1998-403	19980309
	CA 2322395	AA	19990916	CA 1999-2322395	19990308
	AU 9928175	A1	19990927	AU 1999-28175	19990308
	AU 748492	B2	20020606		
	EP 1068164	A2	20010117	EP 1999-908656	19990308
	EP 1068164	B1	20020925		
	R:	AT, BE, CH, DE, DK, ES, FR, GB, GR, IT, LI, NL, SE, PT, IE, SI, LT, LV, FI			
	JP 2002505996	T2	20020226	JP 2000-535601	19990308
	AT 9909129	A	20020915	AT 1999-9129	19990308
	AT 410440	B	20030425		
	AT 224860	E	20021015	AT 1999-908656	19990308
	NO 2000004473	A	20001030	NO 2000-4473	20000907
PRAI	AT 1998-403	A	19980309		
	WO 1999-AT56	W	19990308		

AB The matrixes are produced by depositing on mortar or **concrete** a paint or coating material contg. .gtoreq.1 of (1) aluminosilicates having general formula $aM_2O.bAl_2O_3.cSiO_2$ (c/b ratio 1-40, preferably 5-20; a/b ratio 1-25, preferably 5-15; M = Li, Na, K), (2) an aluminohydroxo complexes having general formula $MxAl(OH)y$ (x = 1-3; y = 4-6; M = Na, K), and (3) Al phosphates, preferably condensed Al phosphates, in combination with addnl. aluminosilicates and water-dispersible org. polymers, to give microcapillary composite matrixes having sp. elec. resistance (measured at the surface) <25, preferably <5 .OMEGA..bul.cm. An elec. conductive paint or coating material, preferably elec. conductive pigments and/or fibers, is applied to the matrix, e.g., **concrete** or mortar. The paint or coating material may contain reactive aluminosilicates, preferably metakaolin, SiO₂ fume, SiO₂ sol, and dispersing agents, thickeners, water-retaining agents, film formers, fillers, and fibrous materials. The coating is resistant to acids and chloride, and extends the service life of porous mineral structures. An elec. conductive coating was prep'd. from (as component A) K silicate soln. (SiO₂ 31.5, K₂O 14.8%) 59, 50% aq. dispersion of carboxylated butadiene-styrene copolymer 208, Bu glycol ether 2.25, graphite powder 180, and deionized water 80, and (as component B) $Na_x[Al(OH)_{3+x}]$ soln. (Al₂O₃ 38.6, Na₂O 54.5%) 5.3 wt. parts. The coating was applied to 1-yr-old mortar in 2 layers to thickness .apprx.300 .mu.m,

and had sp. elec. resistance 0.42 . omEGA. bul. cm.

is corrosion resistant